

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
8 January 2004 (08.01.2004)

PCT

(10) International Publication Number  
**WO 2004/003238 A1**

(51) International Patent Classification<sup>7</sup>:  
D06P 3/32, 1/52

C14C 3/16,

(74) Agent: MAUÉ, Paul Georg; Solvias AG, Patents, WKL-  
402.4.26||Klybeckstrasse 191, CH-4002 Basel (CH).

(21) International Application Number:

PCT/EP2003/050230

(22) International Filing Date: 16 June 2003 (16.06.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

1125/02 28 June 2002 (28.06.2002) CH  
1872/02 7 November 2002 (07.11.2002) CH

(71) Applicant (for all designated States except US): TFL  
LEDERTECHNIK GMBH [DE/DE]; Im Schwarzenbach  
2, 79576 Weil am Rhein (DE).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,  
MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD,  
SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US,  
UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,  
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (for US only): FENNEN, Jens  
[DE/DE]; Stückweg 1, 79639 Grenzach-Wyhlen (DE).  
HERRMANN, Wolfgang [DE/DE]; Johann-von-Weerth-  
strasse 21, 79100 Freiburg (DE). QUENNET, Edith  
[DE/DE]; Im Sonnengarten 5, 79592 Fischingen (DE).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: PROCESS AND AUXILIARIES FOR THE TREATMENT OF ORGANICALLY TANNED LEATHER

(57) Abstract: Organic polyamines having at least three amino groups in the molecule, or mixtures or reaction products (1) of such polyamines with (2) at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group, so that said reaction products have at least two free amino groups in the molecule, said functional group forming a covalently bonded bridging group with an amino group of the polyamine, are suitable as cationic auxiliaries in the finishing of leathers and skins, pretanned with dialdehydes and retanned with organic tanning agents, with anionic auxiliaries, such as, for example, anionic dyes.

Best Available Copy

519,540



WO 2004/003238 A1

## **Process and auxiliaries for the treatment of organically tanned leather**

The present invention relates to a process for the treatment of leather and skins (also referred to below as "wet white" leather), tanned exclusively with dialdehydes and with organic tanning agents, with anionic auxiliaries with addition of organic polyamines, optionally as a mixture with functional alkylsilanes, or with reaction products of organic polyamines and functional alkylsilanes; and mixtures or reaction products of functional alkylsilanes and organic polyamines.

The proportion of leathers tanned exclusively with organic tanning agents has increased continuously in recent years. This is due in particular to the considerable increase in the production of "wet white" leathers. This is understood as meaning a leather which is pretanned with aldehydes, in particular glutaraldehyde, and can be mechanically processed and has a sufficient storage stability. This pretanned leather is then completely tanned with large amounts of anionic synthetic and vegetable retanning agents in order to obtain a final article having the desired performance characteristics, such as body, grain structure, softness and handle.

For the treatment of tanned leathers with anionic auxiliaries, cationic auxiliaries are frequently used for fixing them.

CH-A-676012 proposes long-chain alkylaminoalkylene oxide adducts having esterified terminal hydroxyl groups as auxiliaries for the dyeing of leather, in order to improve the colour fastness. Owing to the reaction with the alkylene oxides, the adducts are considered to be uneconomical. The adducts contain relatively few amino groups, and leather substrates can therefore be pretreated with the adducts without substantially hindering the desired penetration of anionic dyes (positive charge of the leather substrate).

EP-A-0 432 686 describes condensates of polyalkylenepolyamines, alkylated or alkenylated hydroxyaromatics and formaldehyde as auxiliaries for improving the penetration of anionic dyes into the leather. Here too, the leather is treated, prior to dyeing, with a composition which contains relatively few amino groups and with which the dyeing of both the surface and the interior region of the leather substrate is to be achieved.

EP-A-0 057 398 describes polyethers of aminodialkanols as auxiliaries for the aftertreatment of fibre materials having a nonfelting finish, in particular wool.

DE-A3517804 proposes optionally oxaalkylated polyalkylenamines as auxiliaries for dyeing differently tanned, for example chrome tanned or vegetable tanned, leather. The pretanning with dialdehydes and the particular difficulties of the treatment of such leathers with anionic auxiliaries are not discussed.

It has also already been proposed to use functionalized cationic auxiliaries which bind to or are deposited on the fibres of the substrate, in order to avoid these disadvantages. US-A-3,653,952 and WO 00/77292 describe the use of aminoalkylsilanes as dyeing auxiliaries for fibrous materials, including leather. In US-A-3,741,721 aminoalkylsilanes are used for fixing the anionic dye after the dyeing of fibrous substrates. Although improvements are obtained with the aminoalkylsilanes, disadvantages also have to be accepted. The fixing of the dyes is improved but is still insufficient with regard to the colour fastness. Furthermore, it is difficult to obtain a uniform dyeing without redyeing operations. An undesired hardening of the leather surface is also observed. The aminoalkylsilanes have to be used in relatively large amounts, which prevents industrial use owing to the expensive chemicals.

In comparison with chrome leather, which still accounts for by far the predominant proportion of world leather production, wet white leather has a substantially more anionic character. As a result of this, anionic auxiliaries, such as dyes, fatliquoring agents and tanning agents, are fixed considerably more poorly on the substrate. This is evident, inter alia, in the substantially poorer physical fastnesses compared with chrome leather and in the poorer exhaustion of the auxiliary liquors.

To date, the poor fastness to perspiration has prevented more widespread use of wet white leathers. In the case of chrome leathers, the dye fixing, which is in any case better, can be further improved by the use of commercial cationic auxiliaries so that in most cases adequate fastnesses can be achieved. In the case of wet white leathers, this problem is more difficult to solve because many known cationic fixing agents result as a rule in only an insubstantial improvement in the in any case substantially poorer fastness to perspiration.

It has now surprisingly been found that, in the case of leathers pretanned with dialdehydes and retanned with organic (anionic) compositions, considerably stronger fixing of anionic auxiliaries, for example anionic dyes, in comparison with commercial fixing agents is achieved and an unexpectedly substantial improvement of the fastnesses, in particular the fastnesses to perspiration, is achieved if organic polyamines having at least three amino groups in the molecule, or mixtures or reaction products of such polyamines with functional alkylsilanes, are used as fixing agents. Furthermore, by means of such compositions, even a dyeing which is more uniform over the surface and more intense is achieved, hardening of the surface is avoided and in addition a filling and retanning effect is observed in the case of leather.

The invention first relates to a process for the treatment of leathers or skins, pretanned with dialdehydes and retanned with organic tanning agents, with anionic reagents in an aqueous liquor, in which

- a) either an anionic reagent together with at least one organic polyamine having at least three amino groups in the molecule, or mixtures or reaction products (1) of such polyamines with (2) at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group so that said reaction products have at least two free amino groups in the molecule, said functional group forming covalently bonded bridging groups with an amino group of the polyamine, are added to the liquor and allowed to act on the leather,
- b) or the leather is first treated with anionic reagents and then, in the same or a fresh liquor, at least one organic polyamine having at least three amino groups in the molecule, or mixtures or reaction products (1) of such polyamines with (2) at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group so that said reaction products have at least two free amino groups in the molecule, said functional group forming a covalently bonded bridging group with an amino group of the polyamine, is or are allowed to act on the treated material,
- c) or the leather is first treated with an organic polyamine having at least three amino groups in the molecule, or mixtures or reaction products (1) of such polyamines with (2) at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group so that said reaction products have at least two free amino groups in the molecule, said functional group forming a covalently

bonded bridging group with an amino group of the polyamine, and the anionic reagents are then allowed to act on the treated material in the same or a fresh liquor.

The organic polyamines used can be modified with epoxides, for example alkylene oxides or glycidyl ethers, and contain at least one hydroxyalkyl and/or hydroxypolyoxaalkyl group bonded to N atoms. Examples of alkylene oxides are in particular ethylene oxide and propylene oxide. The hydroxypolyoxaalkyl group may contain, for example, 2 to 30, preferably 2 to 20 and particularly preferably 2 to 10, oxaalkylene groups. Such modified polyamines are known and some of them are commercially available. If the polyamines are modified with epoxides, they preferably contain at most up to 20, more preferably up to 10 and particularly preferably up to 5, percent by weight of hydroxyalkyl and/or hydroxypolyoxaalkyl groups, based on the total amount of polyamine and epoxide. In a particularly preferred embodiment, the polyamines are unmodified. Furthermore, the organic polyamines contain no quaternary ammonium groups.

The production of wet white leather is generally known and widely described in the literature, for example by A. Püntener and N. Gschwind in *Das Leder* [Leather], **45**, 18 - 23, 1994, and by G. Wolf, M. Breth, J. Carle and G. Igl in *Journal of the American Leather Chemists Association*, **96**, 111 - 119, 2001. Dialdehydes, for example aliphatic, cycloaliphatic or aromatic dialdehydes, which have altogether 2 to 18, preferably 2 to 12 and particularly preferably 3 to 8, carbon atoms are used for the pretanning of hides and skins. In particular, glutaraldehyde has become established in the industrial production.

Examples of retanning agents are anionic sweetened or unsweetened vegetable tanning agents, anionic and aromatic syntans, anionic polymer tanning agents, polyphosphates, lignin tanning agents, anionic resin tanning agents and anionic polyurethane ionomers and anionic fluorine compounds (*Bibliothek des Leders* [Leather Library], edited by Hans Herfeld, Volume 3 "Gerbmittel, Gerbung, Nachgerbung" [Tanning agents, tanning, retanning], Kurt Faber).

Suitable vegetable tanning agents are, for example, tanning agents which are obtained from constituents of mimosa, quebracho, tara, oak, chestnut, gambir, sumach or spruce. Vegetable tanning agents which contain pyrogallol or pyrocatechol are particularly suitable.

Suitable anionic, aromatic syntans are, for example, those compounds which are obtainable by condensation of sulphonated aromatic compounds alone or together with further, generally unsulphonated aromatic compounds with formaldehyde and/or urea.

Aromatic compounds suitable for this purpose are, for example, naphthalene, biphenyl, terphenyl, phenols, cresols, 4,4'-dihydroxydiphenyl sulphone,  $\beta$ -naphthol, dihydroxybenzenes, resorcinol, 2,2'-bis(hydroxyphenyl)propane and diaryl ethers, such as diphenyl ether and ditolyl ether, which were optionally sulphonated in a manner known per se.

Particularly suitable anionic aromatic syntans are the following compounds:

- (I) condensates of sulphonated phenol or cresol and formaldehyde,
- (II) condensates of naphthalenesulphonic acid and formaldehyde,
- (III) formaldehyde condensates of 4,4'-dihydroxydiphenyl sulphones with arylsulphonic acids or (hydroxy)arylsulphonic acids,
- (IV) formaldehyde condensates of aromatic hydroxy compounds containing sulpho groups with aralkyl halides,
- (V) urea-formaldehyde condensates of phenols and phenolsulphonic acids,
- (VI) reaction products of phenol and a sulphonating agent, the molar (phenol):(SO<sub>3</sub>) ratio being (1):(1.1-2.2),
- (VII) condensates of sulphonated diaryl ethers and formaldehyde,
- (VIII) condensates of sulphonated di- or terphenyls and formaldehyde,
- (IX) condensates of 4,4'-dihydroxydiphenyl sulphone and sulphonated 4,4'-dihydroxydiphenyl sulphone with formaldehyde,
- (X) formaldehyde condensates of diaryl ether sulphonic acids and 4,4'-dihydroxydiphenyl sulphone and
- (XI) formaldehyde condensates of phenol with arylsulphonic acids or hydroxyarylsulphonic acids.

These condensates are present in the form of the free acids, preferably in the form of the sulphonic acids, or as salts, especially ammonium, lithium, potassium or, in particular, sodium salts.

These condensates are known, for example, from Ullmanns Enzyklopädie der technischen Chemie [Ullmann's Encyclopaedia of Industrial Chemistry], Vol. 16, (4), pages 138 to 140 (1979), or can be prepared by the processes described in the references given there.

Suitable resin tanning agents are the anionic compounds which are obtained if condensates of nitrogen-containing organic compounds, such as, for example, urea, thiourea, dicyandiamide or melamine, are condensed with formaldehyde or other simple oxo compounds and anionic compounds, such as, for example, phenols, alkali metal salts of aromatic sulphonic acids, sulphonamides, ligninsulphonates, sulphite or hydrogen sulphite.

The polymeric retanning agents are, for example, poly(meth)acrylates, copolymers containing (meth)acrylates or maleic acid.

These retanning agents are known and many of them are commercially available.

Anionic reagents for the finishing of fibrous materials are, for example, fatliquoring agents, water repellents, retanning agents, dyes and further auxiliaries. Anionic reagents contain at least one acidic group, for example  $\text{COOH}$ ,  $\text{SO}_3\text{H}$ ,  $\text{SO}_2\text{H}$ ,  $\text{PO}(\text{OH})_2$  or  $\text{POOH}$ , which may be present in the form of salts, for example as Na, K or  $\text{NH}_4$  salts.

Anionic auxiliaries are generally added to the liquor in amounts of from 0.1 to 30, preferably 0.1 to 20 and particularly preferably 0.1 to 10, % by weight, based on the shaved weight of the leather or of the skin.

Examples of fatliquoring agents and water repellents are reaction products of animal, vegetable or synthetic fats, oils or waxes which are obtained by means of sulphation, sulphitation, sulphonation, hydrolysis or oxidation; synthetic anionic fatliquoring agents having the abovementioned functional groups; fatliquoring agents and water repellents which contain anionic auxiliaries, for example emulsifiers or polymers having the abovementioned functional groups, and anionic functional silicones or fluorine compounds (Bibliothek des Leders [Leather Library], edited by Hans Herfeld, Volume 4 "Entfetten,

Fetten, Hydrophobieren bei der Lederherstellung" [Degreasing, fatliquoring, imparting water repellency in leather production], Martin Hollstein, and EP 1 087 021 A1).

Examples of further auxiliaries are anionic polymers and aromatic syntans as neutralizing agents or dispersants, phosphoric esters as flameproofing agents and tear strength improvers and amphoteric auxiliaries (Bibliothek des Leders [Leather Library], edited by Hans Herfeld, Volume 3 "Gerbmittel, Gerbung, Nachgerbung" [Tanning agents, tanning, retanning], Kurt Faber).

The process according to the invention is suitable in particular for the dyeing of leathers and skins with anionic dyes, process variant b) preferably being used.

Preferred dyes may correspond to the formula I



in which

dye is the skeleton of a water-soluble, organic or organometallic dye,

X is a direct bond or a divalent bridging group,

Z is an anionic group and

y is a number from 1 to 10.

The bridging group is preferably C<sub>1</sub>-C<sub>12</sub>alkylene, which may be interrupted by O, S or NR, in which R is H or C<sub>1</sub>-C<sub>4</sub>alkyl.

In formula I, X is preferably a direct bond.

In formula I, Z is preferably -OH, -COOH, -SO<sub>3</sub>H and -PO<sub>3</sub>H, and the alkali metal, alkaline earth metal and ammonium salts thereof.

In formula I, y is preferably a number from 1 to 6, particularly preferably from 1 to 4.

Suitable dyes are mentioned in the Colour Index and are familiar to a person skilled in the art. Some examples are Acid Black 210, Direct Black 168, Acid Black 172, Acid Brown 75, Acid Brown 191 and other acid and direct dyes, in particular from the group consisting of the azo dyes and of the azo dyes complexed with metals.



The polyamines to be used according to the invention may be low molecular weight, oligomeric or polymeric compounds which are preferably soluble in polar solvents and also in water. The compounds may have molecular weights of from 60 to 1 000 000, preferably from 100 to 500 000, more preferably from 150 to 200 000 and particularly preferably from 200 to 50 000 Dalton.

The amino groups for the formation of reaction products (free amino groups) may be  $\text{-NH}_2$ ,  $\text{-NH(C}_1\text{-C}_6\text{alkyl)}$  or  $\text{-NH-}$ , and  $\text{-N(C}_1\text{-C}_6\text{alkyl)-}$  or  $\text{-N(C}_1\text{-C}_6\text{alkyl)}_2$  may additionally be present, it being possible for the compounds to contain identical or different amino groups from among these amino groups.  $\text{C}_1\text{-C}_6\text{Alkyl}$  may be linear or branched.  $\text{C}_1\text{-C}_4\text{Alkyl}$  is preferred. Examples of alkyl are methyl, ethyl, n-propyl, isopropyl, n-butyl, pentyl and hexyl. Particularly preferably, the free amino groups are identical or different groups which are selected from  $\text{-NHCH}_3$ ,  $\text{-NHC}_2\text{H}_5$  and particularly preferably  $\text{-NH}_2$  and  $\text{-NH-}$ . Additionally present amino groups are preferably  $\text{-N(CH}_3)_2$ ,  $\text{-N(CH}_3\text{)-}$ ,  $\text{-N(C}_2\text{H}_5)_2$  or  $\text{-N(C}_2\text{H}_5\text{)-}$ .

Depending on the pH of a liquor, the amino groups of the polyamines to be used may be present in the form of salts of inorganic or organic acids, for example formates, acetates, halides (chlorides), sulphates, phosphates, sulphonates or phosphonates.

The low molecular weight polyamines may be saturated or unsaturated, open-chain, mono- or polycyclic compounds which preferably contain 6 to 30, particularly preferably 6 to 20, C atoms and which are unsubstituted or substituted by radicals inert to treatment liquors. The carbon chain may be interrupted by hetero atoms, preferably from the group consisting of  $\text{-O-}$ ,  $\text{-S-}$ ,  $\text{=N-}$  and  $\text{-NR'-}$ , in which  $\text{R'}$  is H,  $\text{C}_1\text{-C}_6\text{alkyl}$ , preferably  $\text{C}_1\text{-C}_4\text{alkyl}$ ,  $\text{C}_5\text{-C}_8\text{cycloalkyl}$ , such as, for example, cyclopentyl, cyclohexyl or cyclooctyl,  $\text{C}_6\text{-C}_{10}\text{aryl}$ , such as, for example, phenyl or naphthyl, or  $\text{C}_7\text{-C}_{12}\text{aralkyl}$ , such as, for example, phenylmethyl or phenylethyl. The low molecular weight polyamines preferably contain 3 to 8, more preferably 3 to 6 and particularly preferably 3 or 4, amino groups, which may also be present as group  $\text{-NR'-}$  in a heterocyclic ring.

Examples of low molecular weight polyamines are propanetriamine, butanetriamine, hexanetriamine, octanetetramine, polyalkylenepolyamines, such as diethylenetriamine, triethylenetetramine, cyclohexanetriamine, cyclooctanetriamine, cyclooctantetramine, diaminopyrrolidine, diaminopiperazine, triaminobenzene, tri- or tetraaminobiphenyl, tri- or tetraaminobiphenyl ether, tri- or tetraaminobiphenyl thioether, tri- or

tetraaminobiphenylamine, tri- or tetraaminonaphthalene, tri- or tetraaminoazobenzene, isophoronetriamine and diaminoindole.

The polyamines having at least 3 amino groups may be oligomers or polymers in which the amino groups are bonded either directly or via a bridging group to the polymer backbone. Such polymers are known and some of them are commercially available. The polymers and oligomers are substantially polymers or polycondensates. The oligomers and polymers may also be those which contain amino groups in the polymer backbone. In the context of the invention, oligomers are understood as meaning polyamines having 3 to 100, preferably 3 to 50 and particularly preferably 3 to 30 identical or different monomer units. The polymers may contain more than 100 and up to about 28 000, preferably up to 14 000 and particularly preferably up to 6 000 identical or different monomer units. They may be homo- or cooligomers or homo- or copolymers.



Oligomeric and polymeric polyamines are known and can be prepared by known processes.

The oligomers and polymers may be derived from monomers containing amino groups, such as, for example, vinylamine, allylamine, 4-aminostyrene, amino-C<sub>2</sub>-C<sub>6</sub>alkyl esters or amino-C<sub>2</sub>-C<sub>6</sub>alkylamides of ethylenically unsaturated carboxylic acids, amino-C<sub>2</sub>-C<sub>6</sub>alkyl ethers of vinyl alcohol and di- or triaminocarboxylic acids, such as lysine. Oligomers or polymers based on such monomers are known or can be prepared in a manner known per se, directly by polymerization or subsequent modification of oligomers or polymers, such as, for example, esterification, transesterification, amidation or transamidation of polymeric unsaturated polycarboxylic acids or their esters and amides with aminoalkyl alcohols or alkyldiamines. Ethers of vinyl alcohols are obtainable by reacting polyvinyl alcohol with aminoalkyl halides or aminoalkyl epoxides. Polyvinylamines are obtainable by polymerization of, for example, vinylacetamide and subsequent hydrolysis. The ethylenically unsaturated carboxylic acids are preferably acrylic acid, methacrylic acid and maleic acid. For the preparation of oligomers, the polymerization can be terminated or a chain terminating agent may be used.

Comonomers suitable for the oligomers and polymers are, for example, C<sub>2</sub>-C<sub>18</sub>alkenes, vinyl chloride, vinylidene chloride, tetrafluoroethylene, styrene, vinylpyrrolidone, maleic acid and esters and amides thereof, acrylic acid and methacrylic acid and esters and amides thereof, vinyl esters and vinyl ethers, and vinylamides of carboxylic acids.

The oligomers and polymers may also contain structural elements of comonomers having other functional groups which are capable of reacting with functional groups of the alkylsilanes. Examples of such functional groups have been mentioned above. In addition, the thiol and in particular the hydroxyl group are suitable. Suitable comonomers are, for example, vinyl alcohol,  $\beta$ -hydroxyethyl vinyl ether,  $\beta$ -hydroxyethyl acrylate,  $\beta$ -hydroxyethyl methacrylate,  $\beta$ -hydroxyethylacrylamide or  $\beta$ -hydroxyethylmethacrylamide. Whether and the extent to which the functional groups react only with amino groups, only with other functional groups or with both types of functional groups depends on the reactivity of said functional groups with respect to other functional groups. This is not essential for the activity of the compounds according to the invention and containing amino groups, since it is mainly the covalent bonding of the alkylsilanes that is important.

Preferred polyamines to be used according to the invention are oligomers and polymers having at least one repeating structural element of the formula II and optionally at least one repeating structural element of the formula III



in which

$R_1$  is H or  $C_1$ - $C_4$ alkyl,

$R_2$  is H or methyl,

$R_3$  is H,  $C_1$ - $C_{17}$ alkyl, phenyl, methylphenyl, pyrrolidinyl, Cl,  $-O-C_1-C_4$ alkyl,  $-O-(CO)-C_1-C_4$ alkyl,  $-C(O)-OR_4$  or  $-C(O)-NR_5R_6$ ,

$R_4$  is H or  $C_1$ - $C_{18}$ alkyl and

$R_5$  and  $R_6$ , independently of one another, are H or  $C_1$ - $C_4$ alkyl.

$R_1$  is preferably H or methyl.  $R_3$  and  $R_4$  as alkyl may be linear or branched.

The amount of structural elements of the formula II may be, for example, from 0.1 to 100 mol%, preferably from 2 to 50 mol%, more preferably from 3 to 30 mol% and particularly preferably from 5 to 20 mol%, based on 1 mol of an oligomer or polymer. The amount of structural elements of the formula III may be, for example, from 0 to 99.9 mol%, preferably from 50 to 98 mol%, more preferably from 70 to 97 mol% and particularly preferably from 80 to 95 mol%, based on 1 mol of an oligomer or polymer. The properties of the oligomers and polymers and the performance characteristics thereof can be influenced by the content of structural elements of the formula III.

Depending on the preparation process, oligomers and polymers may also have different proportions of branches, which however do not present any problems.

In the process according to the invention, oligomers which may contain from 3 to 30, preferably from 3 to 20, more preferably from 3 to 15 and particularly preferably from 3 to 10 structural elements of the formula II and optionally structural elements of the formula III are preferably used. The preferred oligomers may be random mixtures of molecules of different chain length. In a particularly preferred embodiment, these oligomers contain structural elements of the formula II and structural elements of the formula III, it being possible for the content of repeating structural elements of the formula II to be from 1 to 100 mol%, preferably from 5 to 80 mol% and particularly preferably from 5 to 50 mol% and the content of repeating structural elements in formula III accordingly to be from 99 to 0 mol%, preferably from 95 to 20 mol% and particularly preferably from 95 to 5 mol%, based on 1 mol of the oligomer or mixture of oligomers, without including the terminal groups.

The oligomers and polymers to be used according to the invention and having amino groups in the oligomer or polymer backbone may be adducts of aliphatic cyclic amines having 2 to 4, preferably 2 or 3, C atoms in the ring, with organic amines which contain at least two amino groups  $\text{-NH(C}_1\text{-C}_4\text{alkyl)}$  or preferably  $\text{-NH}_2$ . The cyclic amines may be pyrrolidine, azetidine or aziridine, the carbon atoms of which may be substituted by  $\text{C}_1\text{-C}_4\text{alkyl}$ . Aziridine and methylaziridine are particularly preferred. Suitable organic amines are those which contain an organic hydrocarbon radical having 2 to 30, preferably 2 to 20 and particularly preferably 2 to 12 C atoms, which may be interrupted by hetero atoms from the group consisting of  $\text{-O-}$ ,  $\text{-S-}$  or  $\text{-NR'-}$ , and to which at least one, preferably 1 to 6, particularly preferably 1 to 4 and in particular two or three amino groups  $\text{-NH(C}_1\text{-C}_4\text{alkyl)}$  or  $\text{-NH}_2$  are bonded, the group  $\text{-NH}_2$  being preferred.  $\text{R'}$  is H or  $\text{C}_1\text{-C}_4\text{alkyl}$ , for example methyl.

The organic hydrocarbon radical may be aliphatic, cycloaliphatic, aromatic or heteroaromatic radicals, for example C<sub>1</sub>-C<sub>22</sub>alkyl, C<sub>2</sub>-C<sub>22</sub>alkenyl, C<sub>2</sub>-C<sub>22</sub>alkylene, C<sub>4</sub>-C<sub>22</sub>alkenylene, C<sub>3</sub>-C<sub>12</sub>cycloalkyl, C<sub>3</sub>-C<sub>12</sub>heterocycloalkyl having hetero atoms selected from the group consisting of -O-, -S- or -NR'- where R' is H or C<sub>1</sub>-C<sub>4</sub>alkyl, C<sub>1</sub>-C<sub>4</sub>alkylene-C<sub>3</sub>-C<sub>12</sub>cycloalkyl, C<sub>1</sub>-C<sub>4</sub>alkylene-C<sub>3</sub>-C<sub>12</sub>cycloalkyl-C<sub>1</sub>-C<sub>4</sub>alkylene, C<sub>6</sub>-C<sub>12</sub>aryl, C<sub>1</sub>-C<sub>4</sub>alkylene-C<sub>6</sub>-C<sub>12</sub>aryl, C<sub>1</sub>-C<sub>4</sub>alkylene-C<sub>6</sub>-C<sub>12</sub>aryl-C<sub>1</sub>-C<sub>4</sub>alkylene, C<sub>5</sub>-C<sub>11</sub>heteroaryl having hetero atoms selected from the group consisting of -O-, -S- or -NR'- where R' is H or C<sub>1</sub>-C<sub>4</sub>alkyl, C<sub>1</sub>-C<sub>4</sub>alkylene-C<sub>5</sub>-C<sub>11</sub>heteroaryl and C<sub>1</sub>-C<sub>4</sub>alkylene-C<sub>5</sub>-C<sub>11</sub>heteroaryl-C<sub>1</sub>-C<sub>4</sub>alkylene and corresponding trivalent to hexavalent hydrocarbon radicals.

The organic hydrocarbon radical may be unsubstituted or substituted, for example by halogen (F, Cl or Br), C<sub>1</sub>-C<sub>4</sub>alkyl or C<sub>1</sub>-C<sub>4</sub>alkoxy.

Organic amines are known in large numbers to a person skilled in the art. The following may be mentioned as examples: C<sub>1</sub>-C<sub>22</sub>alkylamines (methylamine, ethylamine, octylamine, dodecylamine, octadecylamine, eicosylamine, C<sub>2</sub>-C<sub>22</sub>alkenylamines (fatty amines, such as oleylamine), C<sub>2</sub>-C<sub>22</sub>alkylenediamines (ethylenediamine, 1,2- or 1,3-propylenediamine, butylenediamine, hexylenediamine, octylenediamine, decylenediamine, dodecylenediamine, octadecylenediamine, cyclopentylamine, cyclohexylamine, methylcyclohexylamine, N-methylaminopyrrolidine, aminomethyl- or aminoethylcyclohexane, di(aminomethyl)- or di(aminoethyl)cyclohexane, aminopiperidine, cyclohexylenediamine, aniline, nonylaniline, diaminobenzene, 4,4'-diaminobiphenyl, triaminobenzene and isophoronetriamine.

The preparation of the adducts is generally known. Depending on the reaction conditions and ratio of organic to cyclic amines and number of amino groups in the organic amine, linear and branched products up to dendrimers can form. The molecular weight can be controlled via the addition of chain terminators, for example monoamines, alkanols and thiols. Reaction initiators which effect ring opening of the cyclic amines, for example strongly nucleophilic substances, such as alkali metal alcoholates or alkali metal amides, can be added for accelerating the reaction. In the addition reaction, random oligomers and polymers are formed.

Adducts of organic mono- to tetramines, in particular organic diamines, and aziridine, are preferred. The latter preferably contain repeating structural elements of the formula IV and optionally repeating structural elements of the formula V,



terminal groups  $R_8$  being bonded to the ends of the chains, in which

$R_7$  is  $C_2$ - $C_{12}$ alkylene,  $C_5$ - $C_8$ cycloalkylene or  $C_6$ - $C_{10}$ arylene,

$R_8$  is hydrogen,  $C_1$ - $C_{18}$ alkoxy or  $C_1$ - $C_{18}$ alkylamino and

the  $R_{16}$ , independently of one another, are H or  $C_1$ - $C_4$ alkyl.

$R_7$  as alkylene is preferably  $C_2$ - $C_6$ alkylene and particularly preferably  $C_3$ - $C_4$ alkylene. Some examples of alkylene are ethylene, 1,2- or 1,3-propylene, 1,2-, 1,3- or 1,4-butylenes, pentylene, octylene, decylene and dodecylene. Some examples of  $R_7$  as cycloalkylene are cyclopentylene, cyclohexylene and cyclooctylene. Some examples of  $R_7$  as arylene are phenylene and naphthylene.

$R_8$  is preferably hydrogen.

The adducts having repeating structural elements of the formulae IV and V are in particular polyethylenamines.

The polymers may be random mixtures of molecules of different chain length. In a preferred embodiment, these polymers contain structural elements of the formula IV and structural elements of the formula V, it being possible for the content of repeating structural elements of the formula IV to be from 50 to 99 mol%, preferably from 70 to 97 mol% and particularly preferably from 75 to 90 mol% and the content of repeating structural elements of the formula V accordingly to be from 50 to 1 mol%, preferably from 30 to 3 mol% and particularly preferably from 25 to 10 mol%, based on 1 mol of the polymer.

In the process according to the invention, oligomeric adducts which may contain, for example, from 3 to 100, preferably from 3 to 60, more preferably from 3 to 30 and particularly preferably from 3 to 15 structural elements of the formula IV and optionally structural elements of the formula V are preferably used. The preferred oligomers may be random mixtures of molecules of different chain lengths. In a particularly preferred embodiment, these oligomers contain structural elements of the formula IV and structural elements of the formula V, it being possible for the content of repeating structural elements

of the formula IV to be from 50 to 100 mol%, preferably from 70 to 100 mol% and particularly preferably from 75 to 90 mol% and the content of repeating structural elements of the formula V accordingly to be from 50 to 0 mol%, preferably from 30 to 0 mol% and particularly preferably from 25 to 10 mol%, based on 1 mol of the oligomer or mixtures of oligomers including the terminal groups.

It has furthermore been found that the effect of the polyamines can be further improved if an alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group is additionally concomitantly used, either as a mixture with the polyamine or as a reaction product with the polyamine. Amino groups of the polyamine and the functional group form a covalently bonded bridging group. The amino groups forming a covalently bonded bridging group may be a primary or secondary amino group, such as, for example,  $-\text{NH}_2$ ,  $-\text{NH}-$  or  $-\text{NH}(\text{C}_1\text{-C}_6\text{alkyl})$ , preferably  $-\text{NH}_2$ ,  $-\text{NH}-$  or  $-\text{NH}(\text{C}_1\text{-C}_4\text{alkyl})$ . Examples of alkyl have been mentioned above.  $-\text{NH}_2$ ,  $-\text{NH}-$ ,  $-\text{NH}(\text{CH}_3)$  and  $-\text{NH}(\text{C}_2\text{H}_5)$  are particularly preferred. In order to achieve the improvement according to the invention, less than the stoichiometric amount, based on the amino groups present, of functional silanes is sufficient, which leads to a particularly economical application.

The functional group may comprise those selected from the group consisting of halogen, (Cl, Br), epoxide, cyanate, isocyanate,  $-\text{C}(\text{O})\text{Cl}$ ,  $-\text{C}(\text{O})\text{Br}$ ,  $-\text{C}(\text{O})\text{OR}_9$ ,  $-\text{S}(\text{O})_2\text{OR}_9$ ,  $-\text{P}(\text{O})(\text{OR}_9)_2$ ,  $-\text{P}(\text{O})\text{OR}_9$  or  $-\text{C}(\text{O})\text{NR}_{10}\text{R}_{11}$ , in which  $\text{R}_9$ ,  $\text{R}_{10}$  and  $\text{R}_{11}$ , independently of one another, are H or  $\text{C}_1\text{-C}_4\text{alkyl}$ . Functional groups which are more preferred are selected from the group consisting of epoxide, isocyanate, cyanate,  $-\text{C}(\text{O})\text{Cl}$ ,  $-\text{C}(\text{O})\text{Br}$  and  $-\text{C}(\text{O})\text{OR}_9$ , in which  $\text{R}_9$  is H, methyl or ethyl. The epoxide group and also the group  $-\text{NCO}$  are very particularly preferred. If comonomer units comprising, for example, Cl,  $-\text{NCO}$ ,  $-\text{CO}_2\text{H}$ ,  $-\text{CO}_2\text{Cl}$ ,  $-\text{CO}_2\text{CH}_3$ ,  $-\text{CO}_2\text{C}_2\text{H}_5$  or epoxide groups are present in the polyamines, the functional groups may also be  $-\text{NH}_2$  or  $-\text{OH}$ .

The covalently bonded bridging group formed from amino group and functional group may correspond to the formula  $-\text{NR}_{12}-\text{A}-$ , in which  $\text{R}_{12}$  is H or  $\text{C}_1\text{-C}_6\text{alkyl}$  and A is a bond,  $\text{CH}_2\text{CH}(\text{OH})\text{CH}_2$ ,  $\text{C}(\text{O})-\text{O}$ ,  $\text{CH}_2(\text{CH}_2\text{OH})\text{CH}_2$ ,  $\text{C}(\text{O})-\text{NH}$ ,  $\text{C}(\text{O})$ ,  $\text{P}(\text{O})$ ,  $\text{P}(\text{O})(\text{OR}_1)$  or  $\text{S}(\text{O})_2$ .

The organic oxy radicals bonded to the silicon atom may be  $\text{C}_1\text{-C}_{12}\text{alkoxy}$ , preferably  $\text{C}_1\text{-C}_8\text{alkoxy}$ , particularly preferably  $\text{C}_1\text{-C}_4\text{alkoxy}$ , may be  $\text{C}_5\text{-C}_8\text{cycloalkoxy}$  and preferably cyclopentyloxy or cyclohexyloxy, or may be  $\text{C}_6\text{-C}_{10}\text{aryloxy}$  and preferably phenoxy.

Examples of alkoxy are methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, pentyloxy, hexyloxy, heptyloxy, octyloxy, nonyloxy, decyloxy, undecyloxy and dodecyloxy. Preferred oxy radicals are butoxy, propoxy, ethoxy and in particular methoxy.


The alkyl group of the silane may be C<sub>2</sub>-C<sub>12</sub>alkylene, which may be linear or branched. The alkylene preferably contains from 3 to 8, more preferably from 3 to 6 and particularly preferably from 3 or 4 C atoms. Some examples are ethylene, n-propylene, isopropylene, n-butylene and isobutylene. The alkylene group 1,3-propylene is particularly preferred.

The functional silanes preferably correspond to the formula VI



in which

R<sub>13</sub> is C<sub>1</sub>-C<sub>4</sub>alkyl and in particular methyl, R<sub>14</sub> is -(CH<sub>2</sub>)<sub>3</sub>-O-CH<sub>2</sub>- and X<sub>1</sub> is an epoxide group of the formula



or R<sub>14</sub> is C<sub>2</sub>-C<sub>6</sub>alkylene and preferably 1,3-propylene, and X<sub>1</sub> is -NCO or -C(O)OR<sub>15</sub>, in which R<sub>15</sub> is hydrogen or C<sub>1</sub>-C<sub>4</sub>alkyl.

Functional silanes are known and some of them are commercially available. Some examples are 1-trimethoxysilyl-2-carboxyethane, 1-trimethoxysilyl-3-carboxypropane, 1-trimethoxysilyl-2-chloro- or -bromoethane, 1-trimethoxysilyl-3-chloro- or -bromopropane, 1-trimethoxysilyl-3-carboxamidopropane, 1-trimethoxysilyl-3-carbomethoxypropane, 1-trimethoxysilyl-3-isocyanatopropane, 1-trimethoxysilyl-3-cyanatopropane, 1-trimethoxysilyl-3-chloro-carboxypropane and 1-trimethoxysilyl-3-glycidyloxypropane, which, owing to the reactivity of the epoxide group with respect to amino groups, is particularly preferred.

The invention furthermore relates to a composition comprising (a) at least one low molecular weight, oligomeric or polymeric polyamine having at least 3 amino groups and (b) at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group, said functional group being capable of forming a covalently bonded bridging group with an amino group of the polyamine.



The above embodiments and preferences are applicable to the polyamines and functional alkylsilanes. The compositions are obtainable in a simple manner by mixing organic polyamines with functional alkylsilanes, optionally in a suitable solvent.

The amount of functional alkylsilanes in the composition is preferably from 1 to 60% by weight, more preferably from 2 to 40% by weight and particularly preferably from 3 to 30% by weight, based on the total amount of polyamine and functional alkylsilane.

The invention also relates to a reaction product obtainable by reacting (1) at least one organic polyamine which has at least three amino groups in the molecule with (2) at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group, so that said reaction products have on average at least two free amino groups in the molecule, said functional group forming a covalently bonded bridging group with an amino group of the polyamine, with the exception of 4,7,10-triazadecyl-1-trimethoxysilane.

The above embodiments and preferences are applicable to the polyamines and functional alkylsilanes.

The amount of functional alkylsilanes in the reaction product may be from 1 to 60% by weight, preferably from 2 to 40% by weight, particularly preferably from 3 to 30% by weight, based on the total amount of polyamine and functional alkylsilane. The functional alkylsilanes may be bonded to terminal amino groups or to amino groups bonded to oligomer or polymer chains. The reaction products according to the invention also include those in which not all polyamines have been converted, i.e. mixtures of the reaction products with organic polyamines which have at least three amino groups in the molecule. The amount of polyamines in the mixture depends substantially on the amount of functional alkylsilane used.

Preferred reaction products according to the invention are oligomers and polymers having structural elements of the formula VII and optionally structural elements of the formulae VIII and IX



in which

R<sub>16</sub> is H or C<sub>1</sub>-C<sub>4</sub>alkyl,

R<sub>17</sub> is C<sub>2</sub>-C<sub>6</sub>alkylene,

R<sub>18</sub> is C<sub>1</sub>-C<sub>4</sub>alkyl,

X<sub>2</sub> is a direct bond, -C(O)-, -C(O)-O-, -C(O)-NH-, -CH<sub>2</sub>CH(OH)CH<sub>2</sub>-O- or -CH(CH<sub>2</sub>OH)CH<sub>2</sub>-O-,

R<sub>19</sub> is H or methyl,

R<sub>20</sub> is H, C<sub>1</sub>-C<sub>17</sub>alkyl, phenyl, methylphenyl, pyrrolidinyl, Cl, -O-C<sub>1</sub>-C<sub>4</sub>alkyl, -O-(CO)-C<sub>1</sub>-C<sub>4</sub>alkyl, -C(O)-OR<sub>21</sub> or -C(O)-NR<sub>22</sub>R<sub>23</sub>,

R<sub>21</sub> is H or C<sub>1</sub>-C<sub>18</sub>alkyl and

R<sub>22</sub> and R<sub>23</sub>, independently of one another, are H or C<sub>1</sub>-C<sub>4</sub>alkyl.



A particularly preferred subgroup comprises oligomers having structural elements of the formula I and optionally structural elements of the formula II, in which R<sub>16</sub> is methyl and preferably H, X<sub>2</sub> is -C(O)-NH- and R<sub>17</sub> is 1,3-propylene, or -X<sub>2</sub>-R<sub>17</sub>- is -CH<sub>2</sub>CH(OH)CH<sub>2</sub>-, and R<sub>18</sub> is C<sub>1</sub>-C<sub>4</sub>alkoxy and preferably methyl.


The amount of structural elements of the formula VII may be, for example, from 0.1 to 100 mol%, preferably from 2 to 50 mol%, more preferably from 3 to 30 mol% and particularly preferably from 5 to 20 mol%, based on 1 mol of an oligomer or polymer. The amount of

structural elements of the formula VIII may be, for example, from 0 to 99.9 mol%, preferably from 50 to 98 mol%, more preferably from 70 to 97 mol% and particularly preferably from 80 to 95 mol%, based on 1 mol of an oligomer or polymer. The properties of the oligomers and polymers and the performance characteristics thereof can be influenced by a content of structural elements of the formula IX. The structural elements of the formula IX may replace up to 80 mol%, preferably up to 50 mol%, of the structural elements of the formulae VIII and VII.

Oligomers which may contain from 3 to 30, preferably from 3 to 20, more preferably from 3 to 15 and particularly preferably from 3 to 10 structural elements of the formula VII and optionally structural elements of the formula VIII are preferably used in the process according to the invention. The preferred oligomers may be random mixtures of molecules of different chain length. In a particularly preferred embodiment, these oligomers contain structural elements of the formula VII and structural elements of the formula VIII, it being possible for the content of repeating structural elements of the formula VII to be from 1 to 100 mol%, preferably from 5 to 80 mol% and particularly preferably from 5 to 50 mol% and the content of repeating structural elements of the formula VIII accordingly to be from 99 to 0 mol%, preferably from 95 to 20 mol% and particularly preferably from 95 to 5 mol%, based on 1 mol of the oligomer or mixture of oligomers without inclusion of the terminal groups.

Other preferred reaction products are oligomers and polymers which contain repeating structural elements of the formula X and optionally repeating structural elements of the formulae XI, XII, XIII and/or XIV





and where terminal groups  $\text{R}_{25}$  are bonded to the ends of the oligomer and polymer chains, in which

$\text{R}_{16}$ , independently of one another, are H or  $\text{C}_1\text{-C}_4$ alkyl,

$\text{R}_{17}$  is  $\text{C}_2\text{-C}_6$ alkylene,

$\text{R}_{18}$  is  $\text{C}_1\text{-C}_4$ alkyl,

$\text{X}_2$  is a direct bond,  $\text{-C(O)-}$ ,  $\text{-C(O)-O-}$ ,  $\text{-C(O)-NH-}$ ,  $\text{-CH}_2\text{CH(OH)CH}_2\text{-O-}$  or  $\text{-CH(CH}_2\text{OH)CH}_2\text{-O-}$ ,

$\text{R}_{24}$  is  $\text{C}_2\text{-C}_{12}$ alkylene,  $\text{C}_5\text{-C}_8$ cycloalkylene or  $\text{C}_6\text{-C}_{10}$ arylene and

$\text{R}_{25}$  is hydrogen,  $\text{C}_1\text{-C}_{18}$ alkoxy,  $\text{C}_1\text{-C}_{18}$ alkylamino or the group  $\text{-X}_2\text{-R}_{17}\text{-Si(OR}_{18}\text{)}_3$ .

A particularly preferred subgroup comprises oligomers having structural elements of the formulae X to XIV, in which  $\text{R}_{16}$  is methyl and preferably H,  $\text{X}_2$  is  $\text{-C(O)-NH-}$  and  $\text{R}_{17}$  is 1,3-propylene, or  $\text{-X}_2\text{-R}_{17}\text{-}$  is  $\text{-CH}_2\text{CH(OH)CH}_2\text{-O-(CH}_2\text{)}_3\text{-}$ ,  $\text{R}_{18}$  is  $\text{C}_1\text{-C}_4$ alkoxy and preferably methyl,  $\text{R}_{24}$  is  $\text{C}_2\text{-C}_6$ alkylene and in particular ethylene, and  $\text{R}_{25}$  is hydrogen or the group  $\text{-X}_2\text{-R}_{17}\text{-Si(OR}_{18}\text{)}_3$ .

In the oligomeric and polymeric reaction products according to the invention, alkylsilanes may be bonded to the amino groups of all repeating structural elements. However, it is more advantageous, sufficient for the effect and more economical if only a part of the repeating structural elements contains alkylsilanes in bonded form. The amount of structural elements having bonded alkylsilanes is therefore preferably from 0.1 to 30 mol%, more preferably from 0.5 to 10 mol% and particularly preferably from 1.0 to 5 mol%, based on 1 mol of an oligomer or polymer. Such reaction products are mixtures of polyamines and alkylsilane-modified polyamines.

Preferred reaction products having structural elements of the formulae X to XIV are oligomeric adducts which may contain, for example, from 3 to 100, preferably from 3 to 60, more preferably from 3 to 30 and particularly preferably from 3 to 15 structural elements of

the formulae X, XII and/or XIII and optionally structural elements of the formulae XI and XIV. The preferred oligomers may be random mixtures of molecules of different chain length. In a particularly preferred embodiment, the content of repeating structural elements of the formulae X, XII and XIII is from 1 to 100 mol%, preferably from 5 to 60 mol% and particularly preferably from 5 to 40 mol% and the content of repeating structural elements of the formulae XI and XIV is accordingly from 99 to 0 mol%, preferably from 95 to 40 mol% and particularly preferably from 95 to 60 mol%, based on 1 mol of the oligomer or mixture of oligomers with inclusion of the terminal groups.

The preparation of the reaction products according to the invention, having at least two free amino groups, is effected in a manner known per se, in which (a) at least one amino group of a polyamine which contains at least 3 amino groups altogether, is reacted with (b) functional groups of at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group, with formation of a covalently bonded bridging group. If less than the stoichiometric amount of functional alkylsilane is used, based on reactive amino groups, mixtures of polymeric or oligomeric reaction products may be formed, which mixtures contain the unreacted polyamines and polyamines with bonded alkylsilanes. These mixtures can likewise be used according to the invention for the treatment of wet white with anionic auxiliaries.

Depending on the reactivity of the functional groups, the process can be carried out at from -20 to 200 and preferably from 0 to 100°C. If the functional groups are epoxide or isocyanate, the reaction is advantageously carried out at room temperature.

The reactions can be carried out without or in the presence of an inert solvent, it being possible to use a solvent or mixtures of solvents. Suitable solvents are, for example, aliphatic, cycloaliphatic and aromatic hydrocarbons (pentane, hexane, petroleum ether, cyclohexane, methylcyclohexane, benzene, toluene, xylene), aliphatic halohydrocarbons (methylene chloride, chloroform, di- and tetrachloroethane), nitriles (acetonitrile, propionitrile, benzonitrile), ethers (diethyl ether, dibutyl ether, tert-butyl methyl ether, ethylene glycol dimethyl ether, ethylene glycol diethyl ether, diethylene glycol dimethyl ether, tetrahydrofuran, dioxane, diethylene glycol monomethyl or monoethyl ether), carboxylic esters and lactones (ethyl or methyl acetate, valerolactone), N-substituted lactams (N-methylpyrrolidone), carboxamides (dimethylacetamide, dimethylformamide), acyclic ureas (dimethylimidazoline), sulfoxides and sulphones (dimethyl sulfoxide, dimethyl sulphone,

tetramethylene sulphoxide, tetramethylene sulphone) and alcohols (methanol, ethanol, propanol, butanol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol monobutyl ether, diethylene glycol monomethyl ether, ethylene glycol, diethylene glycol monobutyl ether, 1,3-propanediol, 1,4-butanediol).

The process can be carried out in a simple manner, so that the polyamine and optionally the solvent are initially introduced, the alkylsilane is added either completely or in portions and then stirring is effected to complete the reaction. After the end of the reaction, the reaction product can be isolated by removing the solvent, for example by distillation, optionally in vacuo. The reaction product can also advantageously be used directly in liquors for the treatment of fibrous materials or leather and skins, there being no need to remove the solvent beforehand.

Reaction products according to the invention are also obtainable by polymerization of monomers if the functional group of the alkylsilane is first bonded to the amino group of a polymerizable monomeric amine, and the monomer thus modified is polymerized alone or together with comonomers.

The reaction products according to the invention can be isolated by known methods and, if desired, purified, for example by removal of the solvent, spray-drying, precipitation by addition of nonsolvents and filtration and washing of the residues with nonsolvents.

The reaction products and compositions according to the invention are materials of liquid to solid consistency, which are soluble, emulsifiable or dispersible as microparticles in aqueous liquors for the treatment of wet white. The consistency depends substantially on the molecular weight and on the monomers and comonomers chosen for the oligomers and polymers.

The reaction products, compositions and organic polyamines having at least three free amino groups, according to the invention, are outstandingly suitable as auxiliaries in the ready-to-use finish of wet white in aqueous liquors which have a pH of about 14 to 3.5 and preferably 8 to 4. The reaction products, compositions and organic polyamines can be added as such to the liquors. However, it is more advantageous to use formulations in order to achieve a more rapid distribution in the liquor.

The reaction products and compositions according to the invention are outstandingly suitable as auxiliaries in the ready-to-use finish of fibrous materials, such as, for example, textiles, mineral tanned and optionally retanned leathers or skins in aqueous liquors which have a pH of about 10 to 2.5 and preferably 8 to 3.5. The reaction products, compositions and organic polyamines can be added as such to the liquors.

The invention furthermore relates to a composition comprising (1a) at least one organic polyamine having at least three free amino groups, (1b) at least one reaction product according to the invention or a composition according to the invention, (2) a carrier for the components (1a) and (1b) and (3) optionally further additives.

The abovementioned preferences and embodiments are applicable to the organic polyamines having at least three free amino groups and reaction products and compositions (1b) according to the invention.

The choice of the carrier depends substantially on the desired dosage form. It may comprise solid and preferably liquid carriers. Suitable liquid carriers are solvents or mixtures of solvents, for example those mentioned above. Preferred carriers are alcohols, such as, for example, the C<sub>1</sub>-C<sub>6</sub>alkanols, mono- or diethylene glycol C<sub>1</sub>-C<sub>6</sub>alkyl ethers, C<sub>2</sub>-C<sub>6</sub>diols and ethylene glycol or diethylene glycol. Aqueous solutions of the reaction products or compositions are also particularly advantageous. Acids, for example mineral acids (hydrochloric acid, sulphuric acid, phosphorous acid and phosphoric acid) or organic acids, for example sulphonic acids, phosphonic acids and carboxylic acids, for example formic acid and acetic acid, are expediently concomitantly used here for improving solubility.

The composition according to the invention may be present as a solution, emulsion or dispersion in an organic solvent. Solutions, emulsions and dispersions may additionally contain surfactants or stabilizers, for example in an amount of from 0.1 to 20% by weight, based on the composition. Surfactants are widely known. Neutral surfactants are preferred.

The compositions according to the invention may be present in dilute form or as concentrates. The amount of component (1) may be, for example, from 0.1 to 80% by weight, preferably from 5 to 70% by weight and particularly preferably from 10 to 60% by weight, based on the composition.

The preparation of the composition according to the invention can be effected in a simple manner by dissolving, emulsifying or dispersing the agents in the carrier, optionally with stirring, heating or stirring and heating. Microparticles of solid agents can be prepared in a known manner by means of milling or spray-drying. In the reaction of epoxy-functional or isocyanate-functional alkylsilanes with a polyamine for the formation of reaction products, no reaction auxiliaries need be used, owing to the reactivity of these functional groups with respect to amino groups, so that the reaction products are obtained in high purity. These reaction products can therefore advantageously be used in the solvent used for the reaction, directly in liquors for the treatment of leather or skins.

The composition (formulation) according to the invention is used, for example, in amounts such that the components (1a) or (1b) are present in the liquor in an amount of from 0.1 to 30, preferably from 0.1 to 20, more preferably from 0.1 to 15, particularly preferably from 0.5 to 10 and especially preferably from 0.5 to 5, % by weight, based on the shaved weight of the leather. Polyamines, and compositions or reaction products according to the invention, having a functional silane, are used in the same quantity ranges.

The process according to the invention is particularly suitable for the treatment of leathers and furs pretanned and/or retanned with organic tanning agents in the absence of metals, and in particular wet white.

The process according to the invention can be carried out by a procedure in which the leather is added to an aqueous liquor, and the anionic auxiliary and at the same time an organic polyamine and/or a composition according to the invention or a reaction product is then added to the liquor and allowed to act on the leather. Alternatively, the leather can first be treated in an aqueous acidic liquor with the anionic auxiliary and then with a compound according to the invention which contains amino groups. In this alternative, it may be more expedient to discharge the liquor after the treatment with the anionic auxiliary, optionally to wash the leather and to carry out the treatment with a compound according to the invention which contains amino groups in a fresh aqueous liquor. A further alternative comprises first treating the leather with an organic polyamine and/or a reaction product or composition according to the invention and then allowing the anionic auxiliary to act. In this alternative, it may be more expedient to discharge the liquor after the treatment with the organic polyamine and/or a reaction product/composition according to the invention, optionally to wash the fibrous material and to carry out the treatment with the anionic auxiliary in a fresh



aqueous liquor. The treatment can be carried out at elevated temperatures, for example up to 60°, preferably at about 40°C. However, a treatment at room temperature is often sufficient. The treatment time may be, for example, from 10 minutes to 2 hours, times of less than one hour often being sufficient. After the treatment, aftertreatment is expediently effected by means of the addition of an acid, for example formic acid, and the liquor is then discharged. The leather can then be used for the further finishing for completion.

The invention also relates to the use of organic polyamines having at least three amino groups, a reaction product according to the invention, a composition according to the invention or a composition (formulation) according to the invention as an auxiliary in the finishing of wet white with anionic auxiliaries.

An action of the anionic auxiliary which is uniform over the surface, in a combination with strong fixing to the fibrous substrate, is achieved by means of the process according to the invention. The fibrous materials thus produced are therefore distinguished by excellent wet strength, so that the auxiliaries exhibit virtually no bleeding in the further finishing in the wet process and the properties obtained are retained. The process is moreover very economical since, in relation to the polyamine groups, a considerably smaller amount of silane groups has to be introduced in order to obtain the desired effects. Consequently, other desired properties of the substrate are also influenced only to an insignificant extent, if at all. The exhaustion of the liquor is considerably better. The good fastness to perspiration which can be achieved in the case of wet white leather should be singled out in particular.

The examples which follow illustrate the invention in more detail.

#### A) Preparation of reaction products according to the invention


Example A1: Reaction of an oligomeric ethylenamine with 1-trimethoxysilyl-3-glycidyloxypropane

The polyamine used is a commercial oligomeric ethylenamine which comprises about 0.4 percent by weight of tetramines, about 90.4 percent by weight of pentamines, hexamines and heptamines and about 9% by weight of higher amines. 57.69 parts by weight of diethylene glycol monobutyl ether are initially introduced into a glass flask having a condenser and magnetic stirrer. 38.46 parts of oligomeric polyamine and 3.85 parts by weight of 1-trimethoxysilyl-3-glycidyloxypropane are then added in succession. The clear

solution is stirred for 4 hours at room temperature and is used without further purification in example B2. The course of the reaction can be monitored by means of thin-layer chromatography on thin-layer chromatography sheets pretreated with ammonia (Polygran SIL G/UV<sub>254</sub> Macherey and Nagel), mobile phase water, and subsequent visualization by means of UV light with wavelengths of 254 and 366 nm. A brown, oily product is obtained in quantitative yield.

### B) Use examples

Example B1: Dyeing of leather with the anionic dye of the formula XV



#### a) Dyeing of the leather

100 parts by weight of organically pretanned, retanned, fatliquored and dried leather ('wet white crust') are washed for 30 minutes with 600 parts by weight of water at 40°C and then treated for 5 minutes with 1.5 parts by weight of ammonium bicarbonate and 1 part by weight of a formulation of ethoxylated amines, fatty alcohols and salts of aromatic sulphonic acids, which formulation has a levelling effect (trade name of the formulation: INVADERM B<sup>®</sup>, TFL). Thereafter, 4 parts by weight of the above anionic dye are allowed to act on the leather for 60 minutes, 100 parts by weight of water at 50°C and 2 parts by weight of formic acid are then added and the leather is treated for a further 30 minutes. By adding a further 2 parts by weight of formic acid, the pH is reduced to a value of about 3.3. The action is allowed to continue for a further 30 minutes and the liquor is then removed. The leather is then washed with 600 parts by weight of water at 25°C and the wash water is removed.

b) Treatment with an oligomeric ethylenamine

Fresh liquor is prepared from 600 parts by weight of water at 25°C, and 4 parts by weight of a formulation of 38.5 parts by weight of the polyamine described as starting material in preparation example A1 and 61.5 parts by weight of diethylene glycol monobutyl ether are added and the leather is treated for 30 minutes at 25°C and a pH of about 6 to 7. For reducing the pH to about 3.5, 2 parts by weight of formic acid are then added, said acid being allowed to act for a further 15 minutes. The liquor is then removed again. Finally, the leather is washed with 200 parts by weight of water at 25°C for 10 minutes. A leather which has been dyed black and has - for a leather tanned in the absence of metals - very good wet fastness and which can be finished in the customary manner is obtained.

Example B2: Dyeing of leather with the anionic dye of the formula XV

a) Dyeing of the leather

Analogous to example B1a.

b) Treatment with the reaction product of example A1

Fresh liquor is prepared from 600 parts by weight of water and 4 parts by weight of the formulation (reaction product) described in preparation example A1 and the leather is treated for 30 minutes at 25°C and a pH of about 6 to 7. For reducing the pH to about 3.5, 2 parts by weight of formic acid are then added, said acid being allowed to act for a further 15 minutes. The liquor is then removed again. Finally, the leather is washed with 200 parts by weight of water at 25°C for 10 minutes. A leather which has been dyed black and once again has improved wet fastness compared with the leather obtained according to example B1b and which can be finished in the customary manner is obtained.

Examples B3-B14:

In the examples, the following formulations of polyamines are used (parts are parts by weight):

Formulation F1

A commercial oligomeric ethylenamine which comprises about 0.4 percent by weight of tetramines, about 90.4 percent by weight of pentamines, hexamines and heptamines and about 9% by weight of higher amines is used as the polyamine (polyamine B).

Formulation F2

38.5 parts of polyamine B are neutralized, with cooling in a glass flask having a stirrer and reflux condenser, by slow addition of 31.6 parts of tap water and of 29.9 parts of 85% strength formic acid to a pH of 6.9. The clear solution is stirred and then used without further purification.

Formulation F3

77.0 parts of polyamine B are added to 23.0 parts of diethylene glycol monobutyl ether in a glass flask having a stirrer and reflux condenser. The clear solution is stirred and then used without further purification.

Formulation F4

The polyamine used is an aqueous solution of a commercial modified ethylenamine which has a weight average molar mass of 5 000 g/mol.

Formulation F5

The polyamine used is an aqueous solution of a commercial modified ethylenamine which has a weight average molar mass of 800 g/mol.

Formulation F6

The polyamine used is an aqueous solution of a commercial modified ethylenamine which has a weight average molar mass of 2 000 000 g/mol.

Example B3: Dyeing of leather with anionic dye of the formula XVa) Dyeing of the leather with top dyeing:

200 parts by weight of water are added to 100 parts by weight of organically pretanned leather ('wet white'). After the addition of 0.5 part by weight of sodium formate and 0.5 part by weight of sodium bicarbonate, washing is effected for 10 minutes at 30°C. Tanning is then completed with 5 parts by weight of a commercial synthetic liquid tanning agents at 30°C for 20 minutes. Preliminary fatliquoring is then effected with 5 parts by weight of commercial fatliquoring agents at 30°C for 20 minutes. The leather is then retanned again by the addition of 25 parts by weight of commercial synthetic liquid tanning agents and 4 parts by weight of tara. Directly thereafter, 3 parts by weight of the above anionic dye are allowed to act for 120 minutes at 30°C. The dye is then prefixed with 0.8 part by weight of formic

acid, the pH being reduced to a value of 3.9. After the liquor has been removed, washing is effected with 200 parts by weight of water at 50°C for 10 minutes.

The fatliquoring of the leather is effected in a fresh liquor at 50°C for 60 minutes after the addition of 100 parts by weight of water at 50°C and 14 parts by weight of commercial fatliquoring agents. The fixing with acid is effected in two steps. First, 1 part by weight of formic acid is added at 50°C and, after 30 minutes, a further 1 part by weight of formic acid is added at a constant temperature and allowed to act for 30 minutes. The resulting pH is 3.5 – 3.3. The liquor is then removed.

A fresh liquor is prepared from 200 parts by weight of water (50°C) and 0.3 part by weight of formic acid, in order to treat the leather for 10 minutes. The top dyeing is effected with 1 part by weight of the above anionic dye for 30 minutes. Acidification is then effected with 1 part by weight of formic acid and the liquor is allowed to act for a further 30 minutes, the resulting pH being about 3.0. The liquor is removed and finally the leather is washed with 200 parts by weight of water at 50°C for 10 minutes.

#### b1) Treatment with formulation F1

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 2.3 parts by weight of formulation F1 at 40°C and an action time of 60 minutes. The pH increases slightly to 3.8. Finally, fixing is effected with 1 part by weight of formic acid in 30 minutes. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to examples B3b2 and B3b3 and a more intense dyeing is obtained. Finishing is effected in the customary manner.

#### b2) Treatment with commercial fixing agent

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 2 parts by weight of a conventional commercial fixing agent (trade name SELLAFIX<sup>®</sup> FRD liq.) at 40°C and for an action time of 60 minutes. A leather which has been dyed black and has poorer wet fastness compared with the leather obtained according to examples B3b1, B4b and B5b and a lower intensity of the dye is obtained. Finishing is effected in the customary manner.

**b3) Without fixing agent**

The leather is further processed after the dyeing process without addition of fixing agent. A leather which has been dyed black and has a poorer wet fastness and a poorer dyeing compared with examples B3b1, B4b, B5b and, to a lesser extent, B3b2 is obtained.

**Example B4:** Dyeing of leather with anionic dye of the formula XV**a) Dyeing of the leather with top dyeing**

Analogous to example B3a.

**b) Treatment with formulation F2**

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 4 parts by weight of formulation F2 at 40°C and an action time of 60 minutes. The pH increases slightly to 3.8. Finally, fixing is effected with 1 part by weight of formic acid in 30 minutes. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to examples B3b2 and B3b3 and a more intense dyeing is obtained. Finishing is effected in the customary manner.

**Example B5:** Dyeing of leather with anionic dye of the formula XV**a) Dyeing of the leather with top dyeing**

Analogous to example B3a.

**b) Treatment with formulation F3**

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 2 parts by weight of formulation F3 at 40°C and an action time of 60 minutes. The pH increases slightly to 3.8. Finally, fixing is effected with 1 part by weight of formic acid in 30 minutes. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to examples B3b2 and B3b3 and a more intense dyeing is obtained. Finishing is effected in the customary manner.

**Example B6:** Dyeing of leather with anionic dye of the formula XV**a) Dyeing of the leather with top dyeing**

Analogous to example B3a.

**b) Treatment with formulation F4**

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 3.2 parts by weight of formulation F4 at 40°C and an action time of 60 minutes. The pH increases slightly to 3.7. Finally, fixing is effected with 1 part by weight of formic acid in 30 minutes. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to examples B3b2 and B3b3 and a more intense dyeing is obtained. Finishing is effected in the customary manner.

**Example B7:** Dyeing of leather with anionic dye of the formula XV**a) Dyeing of the leather with top dyeing**

Analogous to example B3a.

**b) Treatment with formulation F5**

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 3.2 parts by weight of formulation F5 at 40°C and an action time of 60 minutes. The pH increases slightly to 4.0. Finally, fixing is effected with 1 part by weight of formic acid in 30 minutes. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to examples B3b2 and B3b3 and a more intense dyeing is obtained. Finishing is effected in the customary manner.

**Example B8:** Dyeing of leather with anionic dye of the formula XV**a) Dyeing of the leather with top dyeing**

Analogous to example B3a.

**b) Treatment with formulation F6**

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 3.2 parts by weight of formulation F6 at 40°C and an action time of 60 minutes. The pH increases slightly to 3.6. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to examples B3b2 and B3b3 and a more intense dyeing is obtained. Finishing is effected in the customary manner.

Example B9: Dyeing of leather with anionic dye of the formula XV

a) Dyeing of the leather without top dyeing

200 parts by weight of water are added to 100 parts by weight of organically pretanned leather ('wet white'). After addition of 0.5 part by weight of sodium formate and 0.5 part by weight of sodium bicarbonate, the liquor is allowed to act for 10 minutes at 30°C. Tanning is then completed with 5 parts by weight of commercial synthetic liquid tanning agents at 30°C for 20 minutes. The preliminary fatliquoring is effected with 5 parts by weight of commercial fatliquoring agents for 20 minutes at 30°C. The leather is then retanned by adding 25 parts by weight of commercial synthetic liquid tanning agents and 4 parts by weight of tara. Directly thereafter, 3 parts by weight of the above anionic dye is allowed to act for 120 minutes at 30°C. The dye is then prefixed with 0.8 part by weight of formic acid, the pH being reduced to a value of 3.9. After the liquor has been removed, washing is effected with 200 parts by weight of water at 50°C for 10 minutes. The fatliquoring of the leather is effected at 50°C for 60 minutes in a fresh liquor after the addition of 100 parts by weight of water at 50°C and 14 parts by weight of commercial fatliquoring agent. The fixing with acid is effected in two steps. First, 1 part by weight of formic acid is added at 50°C and, after 30 minutes, a further 1 part of formic acid is added at 50°C and allowed to act for 30 minutes. The resulting pH is 3.3 – 3.5. The liquor is removed and finally the leather is washed with 200 parts by weight of water at 50°C for 10 minutes.

b1) Treatment with formulation F1

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 1.6 parts by weight of formulation F1 at 40°C and an action time of 60 minutes. The pH increases slightly to 3.8. Finally, fixing is effected with 1 part by weight of formic acid in 30 minutes. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to examples B9c and B9d and a more intense dyeing is obtained. Finishing is effected in the customary manner.

b2) Treatment with commercial fixing agent

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 4 parts by weight of a conventional commercial fixing agent (trade name SELLAFIX® FRD liq.) at 40°C and for an action time of 60 minutes. A leather which has been dyed black and has



poorer wet fastness compared with the leather obtained according to example B9b1 and a lower intensity of the dye is obtained. Finishing is effected in the customary manner.

**b3) Without fixing agent**

The leather is further processed after the dyeing process without addition of fixing agent. A leather which has been dyed black and has a poorer wet fastness and a poorer dyeing compared with examples B9b1, B10b, B11b and, to a lesser extent, B9b2 is obtained.

**Example B10:** Dyeing of leather with anionic dye of the formula XV

**a) Dyeing of the leather without top dyeing**

Analogous to example B9a.

**b) Treatment with formulation F2**

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 4 parts by weight of formulation F2 at 40°C and an action time of 60 minutes. The pH increases slightly to 3.8. Finally, fixing is effected with 1 part by weight of formic acid in 30 minutes. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to examples B9b2 and B9b3 and a more intense dyeing is obtained. Finishing is effected in the customary manner.

**Example 11:** Dyeing of leather with anionic dye of the formula XV

**a) Dyeing of the leather without top dyeing**

Analogous to example B9a.

**b) Treatment with formulation F3**

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 2 parts by weight of formulation F3 at 40°C and an action time of 60 minutes. The pH increases slightly to 3.8. Finally, fixing is effected with 1 part by weight of formic acid in 30 minutes. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to examples B9b2 and B9b3 and a more intense dyeing is obtained. Finishing is effected in the customary manner.

Example B12: Dyeing of leather with anionic dye of the formula XV

a) Dyeing of the leather without top dyeing

Analogous to example B9a.

b) Treatment with formulation F4

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 3.2 parts by weight of formulation F4 at 40°C and an action time of 60 minutes. Finally, fixing is effected with 1 part by weight of formic acid in 30 minutes. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to examples B9b2 and B9b3 and a more intense dyeing is obtained. Finishing is effected in the customary manner.

Example B13: Dyeing of leather with anionic dye of the formula XV

a) Dyeing of the leather without top dyeing

Analogous to example B9a.

b) Treatment with formulation F5

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 3.2 parts by weight of formulation F5 at 40°C and an action time of 60 minutes. The pH increases slightly to 3.8. Finally, fixing is effected with 1 part by weight of formic acid in 30 minutes. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to examples B9b2 and B9b3 and a more intense dyeing is obtained. Finishing is effected in the customary manner.

Example B14: Dyeing of leather with anionic dye of the formula XV

a) Dyeing of the leather without top dyeing

Analogous to example B9a.

b) Treatment with formulation F6

The dyed leather is treated for 10 minutes with 100 parts by weight of water at 40°C and 1 part by weight of formic acid. This is followed by the fixing of the dye by addition of 2 parts by weight of formulation F6 at 40°C and an action time of 60 minutes. Finally, fixing is effected with 1 part by weight of formic acid in 30 minutes. A leather which has been dyed black and has improved wet fastness compared with the leather obtained according to

examples B9b2 and B9b3 and a more intense dyeing is obtained. Finishing is effected in the customary manner.

Example B15: Dyeing of vegetable tanned leather with the anionic dye of the formula XV

a) Dyeing of the leather without top dyeing

600 parts by weight of water are added to 600 parts by weight of vegetable tanned, retanned and fatliquored leather ('crust'). After addition of 0.8 part by weight of oxalic acid, 0.8 part by weight of ethylenediaminetetraacetic acid (EDTA) and 0.8 part by weight of a 30% strength solution of an anionic surfactant in water, the liquor is allowed to act for 60 minutes at 35°C. After the liquor has been discharged, washing is effected with a further 600 parts by weight of water at 25°C for 10 minutes and once again the liquor is discharged. A fresh bath of 300 parts by weight of water and 2 parts by weight of a formulation of ethoxylated fatty amines with fatty alcohols and salts of aromatic sulphonic acids, which formulation has a levelling effect, is allowed to act at 30°C for 10 minutes, and 5 parts by weight of the dye of the formula XV are then added. After 90 minutes, the pH is reduced to a value of 3 by adding 2.5 parts by weight of formic acid. After the dye liquor has been discharged, the fatliquoring is effected in a fresh bath of 400 parts by weight of water at 45°C and 9 parts by weight of commercial fatliquoring agents for 60 minutes. By adding two portions each of 1 part by weight of formic acid, acidification is then effected to a pH of 2.8. The liquor is again discharged, washing is effected with 300 parts by weight of water at 45°C for 10 minutes and the liquor is again discharged.

b1) Treatment with formulation F1

The fixing of the dye is effected in a fresh bath of 300 parts by weight of water by addition of 1.5 parts by weight of formulation F1 at 20°C and for an action time of 30 minutes. The pH is then reduced to a value of 3.7 by adding 2 parts by weight of formic acid. Finally, 2 parts by weight of a sequestering agent are added and allowed to act for 30 minutes. A leather which has been dyed black and has only slightly improved fastness to perspiration compared with the leather obtained according to example B15b2 is obtained. Finishing is effected in the customary manner.

b2) Treatment with commercial fixing agent

The fixing of the dye is effected in a fresh bath of 300 parts by weight of water by addition of 1.5 parts by weight of a commercial fixing agent (trade name SELLA FIX FRD®) at 20°C and for an action time of 30 minutes. Finally, 2 parts by weight of a sequestering agent are

added and allowed to act for 30 minutes. A leather which has been dyed black and has only slightly poorer fastnesses to perspiration compared with the leather obtained according to example B15b1 is obtained. Finishing is effected in the customary manner.

### C) Use examples of performance characteristics

#### Example C1: Testing of the fastness to perspiration

The test is carried out according to ISO 11641 by comparison with the corresponding grey scale. S is the change in the shade of the leather as a result of the test, CO is the soiling of a cotton felt and WO is the soiling of a wool felt. The results are shown in tables 1 and 2.

Table 1:

Example with top dyeing	S	WO	CO
B3b1	4	3-4	3
B4b	3	3	2-3
B5b	3-4	3-4	3
B6b	3-4	3-4	3
B7b	3	3-4	3-4
B8b	3-4	3	3
B3b2 (comparison)	3	1-2	1
B3b3 (comparison)	2	1	1

The rating ranges from 1 to 5, 1 being the poorest rating.

Table 2:



Example without top dyeing	S	WO	CO
B9b	2-3	4	4
B10b	2-3	4	4
B11b	3-4	4	3-4
B12b	4	4	3-4
B13b	3-4	4	4
B14b	4	3-4	2-3
B9b2 (comparison)	2	2-3	1-2
B9b3 (comparison)	2	2-3	1-2
B15b1 (comparison)	4	2-3	1-2
B15b2 (comparison)	3-4	2	1

The rating ranges from 1 to 5, 1 being the poorest rating.

Patent claims:

1. Process for the treatment of leathers or skins, pretanned with dialdehydes and retanned with organic tanning agents, with anionic reagents in an aqueous liquor, in which
  - a) either an anionic reagent together with at least one organic polyamine having at least three amino groups in the molecule, or mixtures or reaction products (1) of such polyamines with (2) at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group so that said reaction products have at least two free amino groups in the molecule, said functional group forming covalently bonded bridging groups with an amino group of the polyamine, are added to the liquor and allowed to act on the leather,
  - b) or the leather is first treated with anionic reagents and then, in the same or a fresh liquor, at least one organic polyamine having at least three amino groups in the molecule, or mixtures or reaction products (1) of such polyamines with (2) at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group so that said reaction products have at least two free amino groups in the molecule, said functional group forming a covalently bonded bridging group with an amino group of the polyamine, is or are allowed to act on the treated material,
  - c) or the leather is first treated with an organic polyamine having at least three amino groups in the molecule, or mixtures or reaction products (1) of such polyamines with (2) at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group so that said reaction products have at least two free amino groups in the molecule, said functional group forming a covalently bonded bridging group with an amino group of the polyamine, and the anionic reagents are then allowed to act on the treated material in the same or a fresh liquor.
2. Process according to Claim 1, characterized in that the anionic reagents are fatliquoring agents, water repellents, organic tanning and retanning agents or dyes which have at least one acidic group.
3. Process according to Claim 1, characterized in that the anionic auxiliaries are used in an amount of from 0.1 to 30% by weight, based on the shaved weight of the leather or the skins.

4. Process according to Claim 1, characterized in that the auxiliary is an anionic dye.
5. Process according to Claim 1, characterized in that the polyamines are low molecular weight, oligomeric or polymeric compounds which are soluble in polar solvents and also in water.
6. Process according to Claim 1, characterized in that the low molecular weight polyamines are saturated or unsaturated, open-chain, mono- or polycyclic compounds which contain 6 to 30 C atoms.
7. Process according to Claim 1, characterized in that the polyamines are oligomers or polymers in which the amino groups are bonded either directly or via a bridging group to the polymer backbone or in the polymer backbone.
8. Process according to Claim 7, characterized in that the oligomers contain from 3 to 100, preferably from 3 to 50 and particularly preferably from 3 to 30 and the polymers more than 100 and up to about 28 000 identical or different monomer units.
9. Process according to Claim 7, characterized in that the oligomers and polymers contain at least one repeating structural element of the formula II and optionally at least one repeating structural element of the formula III



in which

R<sub>1</sub> is H or C<sub>1</sub>-C<sub>4</sub>alkyl,

R<sub>2</sub> is H or methyl,

R<sub>3</sub> is H, C<sub>1</sub>-C<sub>17</sub>alkyl, phenyl, methylphenyl, pyrrolidiny, Cl, -O-C<sub>1</sub>-C<sub>4</sub>alkyl, -O-(CO)-C<sub>1</sub>-C<sub>4</sub>alkyl, -C(O)-OR<sub>4</sub> or -C(O)-NR<sub>5</sub>R<sub>6</sub>,

R<sub>4</sub> is H or C<sub>1</sub>-C<sub>18</sub>alkyl and

R<sub>5</sub> and R<sub>6</sub>, independently of one another, are H or C<sub>1</sub>-C<sub>4</sub>alkyl.

10. Process according to Claim 7, characterized in that the oligomers and polymers are adducts of organic diamines and aziridine or a polyethylenamine.

11. Process according to Claim 10, characterized in that the adducts contain repeating structural elements of the formula IV and optionally repeating structural elements of the formula V



terminal groups R<sub>8</sub> being bonded to the ends of the chains, in which

R<sub>7</sub> is C<sub>2</sub>-C<sub>12</sub>alkylene, C<sub>5</sub>-C<sub>8</sub>cycloalkylene or C<sub>6</sub>-C<sub>10</sub>arylene,

R<sub>8</sub> is hydrogen, C<sub>1</sub>-C<sub>18</sub>alkoxy or C<sub>1</sub>-C<sub>18</sub>alkylamino and

the R<sub>16</sub>, independently of one another, are H or C<sub>1</sub>-C<sub>4</sub>alkyl.

12. Process according to Claim 11, characterized in that the adducts are oligomers having 3 to 15 structural elements of the formula IV and optionally repeating structural elements of the formula V.

13. Process according to Claim 11, characterized in that the content of repeating structural elements of the formula IV is from 50 to 100 mol% and the content of repeating structural elements of the formula V is from 50 to 0 mol%.


14. Process according to Claim 1, characterized in that an alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group is additionally concomitantly used, either as a mixture with the polyamine or as a reaction product with the polyamine, the amino groups of the polyamine and the functional group together forming a covalently bonded bridging group.

15. Process according to Claim 14, characterized in that the functional silane corresponds to the formula VI,



in which

$R_{13}$  is  $C_1$ - $C_4$ alkyl and in particular methyl,  $R_{14}$  is  $-(CH_2)_3-O-CH_2-$  and  $X_1$  is an epoxide group of the formula



or  $R_{14}$  is  $C_2$ - $C_6$ alkylene and  $X_1$  is  $-NCO$  or  $-C(O)OR_{15}$ , in which  $R_{15}$  is hydrogen or  $C_1$ - $C_4$ alkyl.

16. Process according to Claim 15, characterized in that the amount of functional alkylsilanes in the composition with the polyamine is preferably from 1 to 60% by weight, based on the total amount of polyamine and functional alkylsilane.

17. Process according to Claim 1, characterized in that the polyamine or the mixture or reaction product of polyamine and alkylsilane is used in an amount of from 0.1 to 30% by weight, based on the shaved weight of the fibrous material.

18. Process according to Claim 1, which is carried out at from room temperature to  $60^\circ\text{C}$ .

19. Composition comprising (a) at least one low molecular weight, oligomeric or polymeric polyamine having at least 3 amino groups and (b) at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group, said functional group being capable of forming a covalently bonded bridging group with an amino group of the polyamine.

20. Composition according to Claim 19, characterized in that the amount of functional alkylsilanes in the composition is from 1 to 60% by weight, based on the total amount of polyamine and functional alkylsilane.

21. Reaction product obtainable by reacting (1) at least one organic polyamine which has at least three amino groups in the molecule with (2) at least one alkylsilane having organic oxy radicals bonded to the silicon atom and a functional group bonded to the alkyl group, so that



said reaction product has on average at least two free amino groups in the molecule, said functional group forming a covalently bonded bridging group with an amino group of the polyamine, with the exception of 4,7,10-triazadecyl-1-trimethoxysilane.

22. Reaction product according to Claim 21, characterized in that the amount of functional alkylsilanes in the reaction product is from 1 to 60% by weight, based on the total amount of polyamine and functional alkylsilane.

23. Reaction product according to Claim 22, which is an oligomer or polymer having structural elements of the formula VII and optionally structural elements of the formulae VIII and IX



in which

R<sub>16</sub> is H or C<sub>1</sub>-C<sub>4</sub>alkyl,

R<sub>17</sub> is C<sub>2</sub>-C<sub>6</sub>alkylene,

R<sub>18</sub> is C<sub>1</sub>-C<sub>4</sub>alkyl,

X<sub>2</sub> is a direct bond, -C(O)-, -C(O)-O-, -C(O)-NH-, -CH<sub>2</sub>CH(OH)CH<sub>2</sub>-O- or -CH(CH<sub>2</sub>OH)CH<sub>2</sub>-O-,

R<sub>19</sub> is H or methyl,

$R_{20}$  is H,  $C_1$ - $C_{17}$ alkyl, phenyl, methylphenyl, pyrrolidiny, Cl,  $-O-C_1-C_4$ alkyl,  $-O-(CO)-C_1-C_4$ alkyl,  $-C(O)-OR_{21}$  or  $-C(O)-NR_{22}R_{23}$ ,




$R_{21}$  is H or  $C_1$ - $C_{18}$ alkyl, and

$R_{22}$  and  $R_{23}$ , independently of one another, are H or  $C_1$ - $C_4$ alkyl.

24. Reaction product according to Claim 23, characterized in that the amount of structural elements of the formula VII is from 0.1 to 100 mol% and the amount of structural elements of the formula VIII is from 0 to 99.9 mol%, based on 1 mol of an oligomer or polymer.

25. Reaction product according to Claim 23, characterized in that the structural elements of the formula IX replace up to 80 mol% of the structural elements of the formulae VII and VIII.

26. Reaction product according to Claim 21, which is an oligomer or polymer having repeating structural elements of the formula X and optionally repeating structural elements of the formulae XI, XII, XIII and/or XIV



terminal groups  $R_{25}$  being bonded to the ends of the oligomer and polymer chains, in which the  $R_{16}$ , independently of one another, are H or  $C_1$ - $C_4$ alkyl,

R<sub>17</sub> is C<sub>2</sub>-C<sub>6</sub>alkylene,

R<sub>18</sub> is C<sub>1</sub>-C<sub>4</sub>alkyl,

X<sub>2</sub> is a direct bond, -C(O)-, -C(O)-O-, -C(O)-NH-, -CH<sub>2</sub>CH(OH)CH<sub>2</sub>-O- or CH(CH<sub>2</sub>OH)CH<sub>2</sub>-O-,

R<sub>24</sub> is C<sub>2</sub>-C<sub>12</sub>alkylene, C<sub>5</sub>-C<sub>8</sub>cycloalkylene or C<sub>6</sub>-C<sub>10</sub>arylene and

R<sub>25</sub> is hydrogen, C<sub>1</sub>-C<sub>18</sub>alkoxy, C<sub>1</sub>-C<sub>18</sub>alkylamino or the group -X<sub>2</sub>-R<sub>17</sub>-Si(OR<sub>18</sub>)<sub>3</sub>.

27. Reaction product according to Claim 26, characterized in that R<sub>16</sub> is methyl and preferably H, X<sub>2</sub> is -C(O)-NH- and R<sub>17</sub> is 1,3-propylene, or -X<sub>2</sub>-R<sub>17</sub>- is -CH<sub>2</sub>CH(OH)CH<sub>2</sub>-O-(CH<sub>2</sub>)<sub>3</sub>, R<sub>18</sub> is C<sub>1</sub>-C<sub>4</sub>alkoxy and preferably methyl, R<sub>24</sub> is C<sub>2</sub>-C<sub>6</sub>alkylene and in particular ethylene, and R<sub>25</sub> is hydrogen or the group -X<sub>2</sub>-R<sub>17</sub>-Si(OR<sub>18</sub>)<sub>3</sub>.

28. Reaction product according to Claim 26, characterized in that the amount of structural elements with bonded alkylsilanes is from 0.1 to 30 mol%, based on 1 mol of an oligomer or polymer.

29. Reaction product according to Claim 26, which is an oligomeric adduct having from 3 to 100 structural elements of the formulae X, XII and/or XIII and optionally structural elements of the formulae XI and XIV.

30. Reaction product according to Claim 29, characterized in that the content of repeating structural elements of the formulae X, XII and/or XIII is from 1 to 100 mol% and the content of repeating structural elements of the formulae XI and XIV is from 99 to 0 mol%, based on 1 mol of the oligomer with inclusion of the terminal groups.

31. Composition comprising (1a) at least one unmodified organic polyamine having at least three free amino groups, (1b) at least one reaction product according to Claim 21 or a composition according to Claim 19, (2) a carrier for the components (1a) and (1b), and (3) optionally further additives.

32. Composition according to Claim 31, characterized in that the amount of components (1a) or (1b) is from 0.1 to 80% by weight, based on the composition.

33. Composition according to Claim 31, characterized in that the carrier is selected from organic solvents or water with addition of an acid.

34. Use of an organic polyamine having at least three amino groups, of a composition according to Claim 19 or 31 or of a reaction product according to Claim 21 as an auxiliary in the finishing of leathers and skins, pretanned with dialdehydes and retanned with organic tanning agents, with anionic auxiliaries.

# INTERNATIONAL SEARCH REPORT

International Application No.  
PCT/EP 03/50230

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C14C3/16 D06P3/32 D06P1/52

According to International Patent Classification (IPC) or to both national classification and IPC.

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C14C D06P

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 791 214 A (TOMOYASU HIROHIDE ET AL) 13 December 1988 (1988-12-13) column 1, line 53 -column 2, line 28 examples 1-8; table 1 ---	19-26
X	US 3 560 543 A (PLUEDDEMANN EDWIN P) 2 February 1971 (1971-02-02) examples 1,2 ---	19-22
X	EP 0 316 730 A (BAYER AG) 24 May 1989 (1989-05-24) examples 2,3 page 2, line 2 -page 3, line 7 --- -/--	1-8,34

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \* & \* document member of the same patent family

Date of the actual completion of the international search

24 September 2003

Date of mailing of the international search report

06/10/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Neugebauer, U

# INTERNATIONAL SEARCH REPORT

Inter: Application No  
PCT/EP 03/50230

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>WO 00 77292 A (BLC LEATHER TECHNOLOGY CT ;HUDSON ANDREW (GB)) 21 December 2000 (2000-12-21) cited in the application page 3, line 4 -page 5, line 29 example 1</p>	1-34

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 03/50230

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4791214	A	13-12-1988	JP 1771943 C	14-07-1993
			JP 4054713 B	01-09-1992
			JP 62020580 A	29-01-1987
			JP 1617612 C	12-09-1991
			JP 2040256 B	11-09-1990
			JP 62020539 A	29-01-1987
			AU 590298 B2	02-11-1989
			AU 6027586 A	22-01-1987
			DE 3683417 D1	27-02-1992
			EP 0209851 A2	28-01-1987
US 3560543	A	02-02-1971	DE 1908283 A1	13-11-1969
			FR 2002157 A5	17-10-1969
			GB 1227513 A	07-04-1971
EP 0316730	A	24-05-1989	DE 3738962 A1	24-05-1989
			EP 0316730 A2	24-05-1989
WO 0077292	A	21-12-2000	AU 5414900 A	02-01-2001
			EP 1194632 A1	10-04-2002
			WO 0077292 A1	21-12-2000
			ZA 200200254 A	24-07-2002

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**